

**SPECIFICATION SHEET # 1102, TRESTLEWOOD II CHARACTER TIMBERS
June 16th, 2005**

1. Species

Douglas Fir

2. Source

Piling of Lucin Cutoff Railroad Trestle--Great Salt Lake (often the butt ends of said piling)

3. Moisture Content

Water saturated (often with significant air drying)

4. HC/FOHC

Heart Center (HC)

5. Metal/Holes

Trestlewood II Character Timbers can have several holes (often about 1" in diameter) where metal has been removed. Such holes are generally surrounded by streaking black stains.

6. Surfacing

Circle-Sawn (Band-Sawn and S4S also available; if not noted otherwise, Circle-Sawn surfacing is implied)

7. Standard Dimensions

a) Cross-sections: 4x6 to 10x10; b) Lengths: to 16'; c) Target Dimensions: circle-sawn timbers are targeted at full-sawn dimensions; band-sawn and planed timbers are targeted at 1/2" under full-sawn for dimensions listed as less than 6" and 3/4" under full-sawn for dimensions listed as 6" and above; d) Tolerances: circle-sawn timbers are cut to the stated dimensions +/- 1/4"; band-sawn timbers are cut to the stated dimensions +/- 1/8"; planed timbers are planed to the stated dimensions +/- 1/16".

8. Available Dimensions

a) Cross-sections: to 16x16 or 14x18 (larger cross-sections may be possible on a case-by-case basis); b) Lengths: to 32' (longer lengths may be possible on a case-by-case basis); c) Target Dimensions: circle-sawn timbers are targeted at full-sawn dimensions for dimensions to 12" and 1/2" nominal dimensions for dimensions over 12"; band-sawn and planed timbers are targeted at 3/4" under full-sawn; d) Tolerances: circle-sawn timbers are cut to the stated dimensions +/- 1/4"; band-sawn timbers are cut to the stated dimensions +/- 1/8"; and planed timbers are planed to the stated dimensions +/- 1/16". Tolerances can be somewhat greater for timbers wider than 12" and/or longer than 20'.

9. Weight

Typically, approximately 4 pounds per board foot

10. Rustic Nature / Grading

TWII Character Timbers will often be cut from the extreme butt end of Lucin Cutoff piling. The resulting timbers can have bolt holes, staining, substantial butt checking, gouging where metal has been removed and wane. TWII Character Timbers are generally more rustic / rougher in nature than standard TWII timbers/lumber. TWII Character Timbers are not intended for use in structural applications. Grade stamping is not available for these timbers.

11. Stability

Trestlewood II timbers have proven to be stable. Like all wood, undried Trestlewood II will experience some shrinkage and develop seasoning checks as it dries. The drying process also often widens any "prior use checking" associated with Trestlewood II's life of service as railroad trestle piling. Trestlewood II does not, in general, twist or warp as much as green timbers.

12. Salt/Minerals

Trestlewood contains significant amounts of salt and other minerals (often 20%+ by weight), creating special characteristics and/or considerations like those described in the following items.

**SPECIFICATION SHEET # 1102, TRESTLEWOOD II CHARACTER TIMBERS
June 16th, 2005**

13. Color

The coloring of individual Trestlewood II timbers varies widely, from normal Douglas Fir coloring to color combinations unique to Trestlewood II. Surfacing and finishes impact final timber coloring. Color variations are more noticeable in planed timbers than in circle-sawn or band-sawn timbers.

14. Finishes/Glues

Certain finishes and glues do not work well with Trestlewood II. Most importantly, **DO NOT USE WATER-BASED FINISHES.**

15. Fire Retardance

Schuller International performed an ASTM E-84 Flame Spread test on a Trestlewood II piling sample in January, 1995. The resulting index value was 16, well below the maximum index value of 25 for a Class I fire retardant. Normal Douglas Fir has a flame spread index of 70 to 100. Only a few wood species have flame spread index values less than 75. Fire retardant treatments are generally necessary to meet Class I (and often to meet Class II.) Trestlewood has not done any tests to determine whether the fire retardant qualities (if any) of material cut from the butt-ends of the piling differ from the fire retardant qualities of material cut from below-water piling materials.

16. Metal Corrosiveness

Trestlewood II can have a corrosive effect on metal fasteners, machinery and saw blades. Stainless steel fasteners should be used in lieu of regular steel fasteners, especially in applications involving the likely mixing of Trestlewood II, moisture and oxygen.

17. Moisture

Trestlewood II absorbs moisture more readily than typical Douglas Fir. Trestlewood II timbers (especially timbers with air dry time) should be handled, stored and transported carefully to minimize any unnecessary reabsorption of moisture.

18. Odor

Wet Trestlewood II timbers often have a Great Salt Lake smell to them. This odor is especially strong as wet timbers are being cut or otherwise processed. It tends to become less and less of an issue as timbers are allowed to air dry.

19. Salt Leaching

As moisture is drawn out of Trestlewood II timbers, it brings salt with it. Salt leaching tends to be the most concentrated at knots and timber ends, but can happen anywhere. Air dry time reduces, but does not eliminate, salt leaching. Approaches to salt leaching include sanding and refinishing impacted areas to doing nothing (and letting the salt serve as one of the most visible evidences of the history and reclaimed nature of Trestlewood II timbers.) Salt is more visible on planed timbers than on circle-sawn or band-sawn timbers.

20. Additional Information

See the current Trestlewood II Features/Issues summary for additional information about Trestlewood II characteristics and their practical implications. This summary is for informational purposes only and is not a part of the Trestlewood II timbers specification sheet.