



SPECIFICATION SHEET # 2202, DOUGLAS FIR CLASSIC MILLWORK STOCK
April 4th, 2008

1. Species

Douglas Fir.

2. Source

Various, often buildings and industrial structures from different locations in North America

3. Moisture Content/Stability

Kiln-Dried. Douglas Fir Classic Millwork Stock is generally cut from stock which is very dry and seasoned and is therefore much more stable and less prone to shrinkage than is new lumber.

4. Knots

Unlimited knots are allowed in Douglas Fir Classic Millwork Stock. Knots may be tight, loose or fallen out.

5. Nail/Bolt Holes

Unlimited nail holes; occasional bolt holes; staining around the nail holes or on the face is allowable

6. Checking/Cracks

Moderate amounts of surface checking allowed; no cracks

7. Grain Pattern

Vertical, Flat or Mixed

8. Standard Dimensions

a) Thickness (net): 4/4"; b) Width (nominal): 4"-10"; actual widths typically are 1/2" under listed width (6" boards would typically be edged to 5 1/2", and billed as 6" for example); and c) Length: random, in 1' increments up to 16'

9. Surfacing

Band-Sawn

10. Weight

Typically, approximately 3 pounds per board foot

11. Other

Unless otherwise specified, all of the above characteristics apply to the board's best face