

**SPECIFICATION SHEET # 3222, CLASSIC HEART PINE MILLWORK STOCK
October 18th, 2006**

1. Species

Southern Yellow Pine/Heart Pine

2. Source

Hammonds Cold Storage Building, Chicago and other reclaimed wood projects from different locations in North America

3. Moisture Content/Stability

Kiln-Dried.

4. Knots

1 tight knot (1" or under) every 1 square foot allowed (on a 1x6 board, this would translate into 1 tight knot every 2 linear feet); larger knots in lower frequency allowed (for example, a 2" knot in 2 square feet that is otherwise clear would be allowed); 2" maximum knot size

5. Nail/Bolt Holes

Occasional random nail holes and bolt holes; some staining around the nail holes and bolt holes or on the face is allowable.

6. Checking/Cracks

Moderate amounts of surface checking allowed; no cracks

7. Grain Pattern

Tight grain. Vertical, Flat or Mixed

8. Heart Content

At least 80% (taken collectively)

9. Standard Dimensions

a) Thickness (net): 4/4"; b) Width: Various; most common widths are 6" and 8" (nominal); actual widths typically range from 1/2" under listed width to full listed width (6" and 8" boards would typically measure from 5 1/2" to 6" and from 7 1/2" to 8", respectively); and c) Length: 2' increments, up to 16'

10. Surfacing

Band-Sawn

11. Weight

Typically, approximately 3 pounds per board foot

12. Other

Unless otherwise specified, all of the above characteristics apply to the board's best face