

SPECIFICATION SHEET # 4235, RESCUED FIR CIRCLE-SAWN LUMBER
April 4th, 2008

1. Species

Mixed Species. May include Douglas Fir, Alpine Fir, White Fir and other Firs.

2. Source

Salvage logging tracts from different locations in North America. This material is processed from new logs which were cut from tracts made available for logging because of forest fires or beetle or other insect infestations. The tracts were opened to logging because the trees were dead or dying, though not every individual tree was dead before being cut down.

3. Moisture Content/Stability

The moisture content in Rescued Fir Circlesawn Lumber will vary from piece to piece. This material is often cut many months before being sold, but should not be considered as stable as reclaimed material.

4. Knots

Unlimited knots; some tight, some fallen out

5. Metal/Holes

Minimal.

6. Checking/Cracks

Unlimited as long as board is sound; end cracks to extend no more than 12" into board.

7. Grain

Mixed grain

8. Surfacing/Coloring

Circle-sawn. The coloration will vary from piece to piece depending on species and stain from bugs or blight.

9. Standard Dimensions

a) Thickness: 1"-2"; b) Width: random, 4" to 12" (actual: up to 1/2" nominal)--widths are heavy to 4", 6", 8" and 10"; Lengths: 2' increments from 8' to 20'.

10. Weight

Depending on species mix. Typically, Rescued Fir Circlesawn Lumber weighs approximately 2.5 pounds per boardfoot.