

SPECIFICATION SHEET # 6012, GREENHEART T&G FLOORING
April 4th, 2008

1. Species

Greenheart

2. Source

The floors of reclaimed railroad boxcars

3. Moisture Content/Stability

Kiln-Dried: Greenheart T&G Flooring is cut from stock which is very dry and seasoned and is then kiln-dried. The resulting lumber is much more stable and less prone to shrinkage than is new Greenheart lumber.

4. Knots

Greenheart T&G Flooring is not sorted for knots, but there are very few knots.

5. Holes

The Greenheart material was fastened onto the boxcars with screws which, when removed, leave very regular screw holes. There is often stain or discoloration around the screw holes.

6. Checking/Cracks

Surface checking is common; end cracking is rare and does not exceed 6" from the end.

7. Grain Pattern

Mixed

8. Standard Dimensions

a) Thickness (net): 3/4"; b) Width: 3"; and c) Length: 3'.

9. Surfacing

Smooth or Circlesawn

10. Color/Appearance

Greenheart is sorted into two color groups: brownish and reddish. Please ask your Trestlewood representative for pictures and samples of the two color groups.

11. Weight

Typically, approximately 4 pounds per board foot