

**SPECIFICATION SHEET # 6203, RESCUED MAPLE MILLWORK STOCK  
November 30th, 2005**

**1. Species**

Primarily Maple

**2. Source**

Sawmill offcuts which have weathered out of grade

**3. Moisture Content**

Kiln-Dried.

**4. Knots**

Unlimited. Some knots are loose, broken or fallen out.

**5. Nail/Bolt Holes**

Essentially none.

**6. Checking/Cracks**

Surface checking is allowed; some cracking is allowed as long as board is sound.

**7. Grain Pattern**

Primarily Flat Sawn

**8. Standard Dimensions**

a) Thickness (net): 4/4"; b) Width: Random, primarily 3" to 7"; most common widths are 5" and 6"; actual widths typically range from 1/2" under listed width to full listed width; small amounts of wider boards (8 to 9" and 10"+) are sometimes available; and c) Length: Primarily 4 to 8'

**9. Surfacing/Color**

Circle-Sawn and then Weathered; some boards are more weathered than others; in general, boards have a nice aged appearance, ranging from silver to brown to black; some boards are water-stained; some boards have some dirt on one or both faces; some boards have been end-trimmed to remove rot and/or damaged ends and/or nails.

**10. Weight**

Typically, approximately 3.5 pounds per board foot

**11. Other**

Unless otherwise specified, all of the above characteristics apply to the board's best face