

SPECIFICATION SHEET # 6205, RESCUED MIXED HARDWOOD MILLWORK STOCK
April 4th, 2008

1. Species

Mixed Hardwoods, can include Hickory, Maple, Ash, Oak, Beech, Elm and others.

2. Source

Sawmill offcuts which have weathered out of grade

3. Moisture Content

Kiln-Dried.

4. Knots

Unlimited. Some knots are loose, broken or fallen out.

5. Nail/Bolt Holes

Minimal

6. Checking/Cracks

Surface checking is allowed; some cracking is allowed as long as board is sound.

7. Grain Pattern

Primarily Flat Sawn

8. Standard Dimensions

a) Thickness (net): 4/4"; b) Width: Random, primarily 3" to 7"; most common widths are 5" and 6"; actual widths typically range from 1/2" under listed width to full listed width; small amounts of wider boards (8 to 9" and 10"+) are sometimes available; and c) Length: Primarily 4 to 8'

9. Surfacing/Color

Circle-Sawn and then Weathered; some boards are more weathered than others; in general, boards have a nice aged appearance, ranging from silver to brown to black; some boards are water-stained; some boards have some dirt on one or both faces; some boards have been end-trimmed to remove rot and/or damaged ends and/or nails.

10. Weight

Typically, approximately 3.5 pounds per board foot

11. Other

Unless otherwise specified, all of the above characteristics apply to the board's best face