



SPECIFICATION SHEET # 6211, RECLAIMED OAK MILLWORK STOCK
January 18th, 2007

1. Species

Oak (White Oak and Red Oak mixed)

2. Source

Barns, corncribs, stables, mills, homes and other buildings
and agricultural structures from different locations in North America

3. Moisture Content/Stability

Kiln-Dried: Reclaimed Oak Millwork Stock is cut from stock which is generally very dry and seasoned and is then kiln-dried. The resulting lumber is much more stable and less prone to shrinkage than is green lumber.

4. Knots

Unlimited. Some knots are loose, broken or fallen out.

5. Nail Holes

Nails and other fasteners are removed, leaving occasional nail holes. Staining around nail and fastener holes is common.

6. Checking/Cracks

Surface checking is allowed; some cracking is allowed as long as board is sound.

7. Grain Pattern

Mixed

8. Standard Dimensions

a) Thickness (net): 4/4"; b) Standard Width: Random, 3" to 6"; most common widths are 5" and 6"; material is edged to 1/2" under listed width; wider boards (7 to 10"+) are available (please request quote); and c) Length: 1' increments up to 16'.

9. Surfacing

Band-Sawn. Weathered Reclaimed Oak will have at least one weathered face.

10. Color/Appearance

Some boards are more rustic than others; in general, boards have a nice aged appearance, with checking, knots, nail holes, stain, some water-stain, etc. (all in varying degrees).

11. Weight

Typically, approximately 4 pounds per board foot

12. Other

Unless otherwise specified, all of the above characteristics apply to the board's best face