

**SPECIFICATION SHEET # 6222, RECLAIMED CHESTNUT MILLWORK STOCK
March 4th, 2005**

1. Species

Chestnut

2. Source

Barns, corncribs, stables, mills, homes and other buildings
and agricultural structures from different locations in North America

3. Moisture Content/Stability

Kiln-Dried: Reclaimed Chestnut Millwork Stock is cut from stock which is generally very dry and seasoned and is then kiln-dried. The resulting lumber is much more stable and less prone to shrinkage than is green lumber.

4. Knots

Unlimited. Some knots are loose, broken or fallen out.

5. Nail Holes

Nails and other fasteners are removed, leaving occasional nail holes. Staining around nail and fastener holes is common.

6. Worm Holes

Reclaimed Chestnut Millwork Stock may have worm holes. The extent of worm holes will vary from none to extensive depending on the piece.

7. Checking/Cracks

Surface checking is allowed; some cracking is allowed as long as board is sound.

8. Grain Pattern

Mixed

9. Standard Dimensions

a) Thickness (net): 4/4"; b) Width: Random, primarily 4" to 8"; most common widths are 5"-7"; actual widths typically range from 1/2" under listed width to full listed width; small amounts of wider boards (8 to 9" and 10"+) are sometimes available; and c) Length: 1' increments up to 12'.

10. Surfacing

Band-Sawn or Weathered

11. Color/Appearance

Some boards are more rustic than others; in general, boards have a nice aged appearance, with checking, knots, nail holes, stain, some water-stain, etc. (all in varying degrees).

12. Weight

Typically, approximately 3 pounds per board foot

13. Other

Unless otherwise specified, all of the above characteristics apply to the board's best face