

**SPECIFICATION SHEET # 7130, WEATHERED RESCUED TIMBERS  
April 4th, 2008**

**1. Species**

Mixed Species. May include Douglas Fir, Alpine Fir, White Fir, Lodgepole Pine, Ponderosa Pine, others.

**2. Source**

Salvage logging tracts from different locations in North America. This material is processed from new logs which were cut from tracts made available for logging because of forest fires or beetle or other insect infestations. The tracts were opened to logging because the trees were dead or dying, though not every individual tree was dead before being cut down.

**3. Moisture Content/Stability**

The moisture content in Weathered Rescued Timbers will vary from piece to piece. This material is cut and then weathered for many months before being sold. This material should not be considered as stable as reclaimed material, but should be more stable than green material.

**4. HC/FOHC**

Generally HC.

**5. Metal**

None.

**6. Holes**

Weathered Rescued Timbers may have nail holes and bolt holes from prior use. Some of this material is used as dunnage and has other materials nailed to it and some other timbers are used as mats and are bolted together with steel rods. The holes will generally have staining around them.

**7. Checking/Cracks**

Timbers generally have checks from the heart center to the faces of the timber. In addition, timbers can have surface checking and cracks, moderate butt checking and minor end splitting.

**8. Surfacing**

Weathered

**9. Standard Dimensions**

a) Cross-sections: 4x6 to 12x12; b) Lengths: to 20';  
c) Target Dimensions: Weathered Rescued Timbers are targeted at full dimension; d) Tolerances: +/- 1/4" (plus whatever shrinkage the material experiences over time).

**10. Appearance Variation**

Weathered Rescued Timbers are cut from different species and from logs that may vary in appearance from piece to piece. As a result, timber characteristics can be expected to vary from piece to piece. Trestlewood believes that appearance variations (no two timbers exactly alike) are one of the selling points of this product line.

**11. Weight**

Typically, approximately 3 pounds per board foot

**12. Grading/Strength**

Weathered Rescued Timbers can be graded (WLCB) upon request. It is highly recommended that any timbers that are to be used in a structural application be graded. It is also recommended that standard size timbers be used whenever possible. Checking tends to be more pronounced in timbers wider and/or thicker than 12" than in standard size timbers.