

### **Species**

Primarily Southern Yellow Pine

### **Source**

Buildings and industrial structures from different locations in North America

### **HC/FOHC**

Generally HC; usually moderate to tight growth rings.

### **Metal**

Nails, bolts and other fasteners are removed or occasionally cut flush or broken off inside the material.

### **Holes**

Nail, bolt and other fastener holes are allowed; the quantity and size of the holes can vary widely from timber to timber, with some timbers containing no holes or only limited small nail holes and others containing frequent nail and bolt holes. Staining around nail and bolt holes is common.

### **Checking/Cracks**

Timbers generally have a check from the heart center to one of the faces of the timber. In addition, timbers can have surface checking and cracks, moderate butt checking and minor end splitting.

### **Moisture Content/Stability**

Air-Dried

### **Surfacing**

Band-Sawn or Planed (S4S)

### **Standard Dimensions**

a) Cross-sections: 4x6 to 10x10; b) Lengths: to 16';  
c) Target Dimensions: timbers are targeted at 1/2" under full-sawn for dimensions up to 5" and 3/4" under full-sawn for dimensions over 5"; d) Tolerances: band-sawn +/- 1/8"; planed timbers +/- 1/16".

### **Available Dimensions**

a) Cross-sections: depending on inventory in stock; b) Lengths: depending on inventory in stock; c) Target Dimensions: timbers are targeted at 3/4" under full-sawn; d) Tolerances: all larger timbers are cut to the stated dimensions +/- 1/8".

### **Weight**

Typically, approximately 3.5 to 4 pounds per board foot

### **Appearance Variation**

Resawn Antique Pine Timbers are often cut from stock coming from a variety of sources. As a result, timber characteristics can be expected to vary from piece to piece. Trestlewood believes that appearance variations (no two timbers exactly alike) are one of the selling points of this product line.

