

Species

Southern Yellow Pine/Heart Pine

Source

Hammonds Cold Storage Building, Chicago and other reclaimed wood projects from different locations in North America

Heart Content

At least 80% (taken collectively)

Holes

Occasional random nail holes and bolt holes; some staining around the nail holes and bolt holes or on the face is allowable. "Naily" material has frequent nail holes on each piece.

Knots

1 tight knot (1" or under) every 1 square foot allowed (on a 1x6 board, this would translate into 1 tight knot every 2 linear feet); larger knots in lower frequency allowed (for example, a 2" knot in 2 square feet that is otherwise clear would be allowed); 2" maximum knot size

Checking/Cracks

Moderate amounts of surface checking allowed; no cracks

Grain Pattern

Tight grain; Vertical, Flat or Mixed

Moisture Content/Stability

Kiln-Dried

Standard Dimensions

a) Thickness (net): 4/4"; b) Width: Various; most common widths are 6" and 8" (nominal); actual widths typically range from 1/2" under listed width to full listed width (6" and 8" boards would typically measure from 5 1/2" to 6" and from 7 1/2" to 8", respectively); and c) Length: 2' increments, up to 16'

Surfacing

Band-Sawn

Weight

Typically, approximately four pounds per board foot

Appearance Variation

Boards can vary in appearance from piece to piece and even within a piece. The characteristics described on this specification sheet generally apply to each board's featured face. The opposite face and edges can differ from the featured face in texture, coloring, and other characteristics unless otherwise noted.

